



FORTIS® 450 Exterior Semi-Gloss Paint 6407-XXXXV

Previously ICI Paints DULUX® FORTIS®
Premium 100% Acrylic Semi-Gloss Exterior Enamel

DESCRIPTION

Our finest exterior product warranted for life, **GLIDDEN PROFESSIONAL™ FORTIS® 450** Exterior Semi-Gloss Paint utilizes the most advanced technology available to provide longer lasting beauty and protection, it provides a mold and mildew resistant coating that has easy one-coat application, excellent adhesion, exceptional weathering resistance, outstanding block resistance and quick curing, even at temperatures as low as 35°F. Ideal for properly prepared wood siding, trim and sash, shakes, shingles, masonry, weathered aluminum siding, weathered vinyl siding, primed metal and sound painted surfaces.

CERTIFICATIONS

AS OF 7/1/2009, COMPLIES WITH	
MPI#	11
LEED	N/A
CHPS	No
GREENGUARD	No
AIM	Yes
OTC/LADCO	Yes
CARB	Yes
SCAQMD	Yes

PERFORMANCE DATA

CHARACTERISTIC:	RESULTS:
Early Moisture Resistance*	★★★★★☆☆☆
Dry Hide*	★★★★★★★★★★
Efflorescence Resistance*	★★★★★☆☆☆
Chalk Adhesion*	★★★★★★★★☆☆
Mildew Resistance*	★★★★★☆☆☆
Weathering*	★★★★★★★★★★
Sag Resistance	20-30 mils wet
Air and Substrate Application Temperature	35°F (2°C) - 90° F (32° C)
Service Temperature Limits	200° F (93° C)
Storage Temperature	40°F (4°C) - 95° F (35° C)

*Performance ratings are based on product comparisons to other products in that sheen range, performed at 77° F (25° C) 50% RH. Rating scale is from 1-10, 10 being the highest rating.

COMPOSITION

- 100% Acrylic Resin for superior performance and durability
- No Alkyd or Vinyl-Acrylic Resins
- High Level of Titanium Dioxide
- Not manufactured with lead or mercury containing materials.

SPECIFICATION

Color:

White, ready mix whites & custom colors

Clean-up Solvent:

Soap and water

Finish: Semi-Gloss

Gloss: 40 - 65 units @ 60°

Density:

10.44 lbs/gal (1.25 kg/L)

Solids:

Volume - 37% +/- 1%

Weight - 50% +/- 1%

VOC:

50 g/L (0.42 lbs/gal) maximum
Refer to MSDS for regulatory VOC content of complete product line

Theoretical Coverage @ 1 mil dry:

586 sq ft/gal (14 m²/L)

Practical Coverage:

Apply at 500-550 sq ft/gal (12-13 m²/L).
Actual coverage may vary depending on substrate and application method.

Recommended Film Thickness:

2.9 - 3.2 mils wet

1.1 - 1.2 mils dry

Airless Spray Application:

Pressure - 2000 psi

Tip - .015" - .019"

Dry Time:

77°F (25°C) & 50% RH

To touch - 1 hour

To recoat - 4 hours

35°F (2°C)

To touch - 3-6 hours

To recoat - 24 hours

Flame Spread Rating:

Class A (0-25) on non-combustible surfaces

Flash Point:

None

Shelf Life:

1 year minimum - unopened



www.gliddenprofessional.com

9 FINISHES
PAINTING (00900)



SURFACE PREPARATION

GENERAL SURFACE PREPARATION:

All surfaces must be sound, dry, clean and free of oil, grease, dirt, rust, mildew, form release agents, curing compounds, loose and flaking paint and other foreign substances.

NEW SURFACES:

Wood:

- Spot prime pine knots with 6001 Hydrosealer Exterior Primer
- Countersink nails, prime entire surface with 6001 Hydrosealer Exterior Primer
- Product may be used self-priming on wood used as a primer under itself
- Slight discoloration on staining woods such as redwood or cedar is normal
- If discoloration is considerable, apply a second coat of 6001 Hydrosealer Exterior Primer or for improved protection prime with 2110 Stain Stomper Exterior Primer Sealer
- Caulk with an acrylic caulk

Preprimed and Unprimed Hardboard:

- Prime entire surface and all edges with 6001 Hydrosealer Exterior Primer or 2110 Stain Stomper Exterior Primer Sealer
- Caulk with an acrylic caulk

Steel, Galvanized Metal and Aluminum:

- Performance over hand or power tool cleaned surfaces is dependent on the degree of cleaning
- Clean off oils and other contaminants
- Prime with Devflex 4020PF Direct-to-Metal Primer, DEVGUARD® 4360 Low VOC Universal Primer or DEVGUARD 4160 Multi-Purpose Tank & Structural Primer

Concrete, Masonry and Stucco:

- Cure at least 30 days before painting
- pH must be 10.0 or lower
- Roughen slick poured or precast concrete and remove sealers by chemical cleaning or abrasive method such as sandsweeping
- Rinse thoroughly with water and allow to dry
- Remove loose aggregate
- Prime with 6001 Hydrosealer Exterior Primer
- Product may be used self-priming on concrete, used as a primer under itself
- Fill concrete block with 3010 Concrete Coatings Block Filler

Fiber Cement Board:

- Prime entire surface and all edges with 6001 Hydrosealer Exterior Primer
- Caulk with an acrylic caulk
- Product may be used self-priming on fiber cement board, used as a primer under itself
- Product may be used directly over preprimed fiber cement siding; two coats are recommended for maximum durability

PREVIOUSLY PAINTED SURFACES:

- Wash to remove contaminants
- Rinse thoroughly with water and allow to dry
- Dull glossy areas by light sanding
- Remove sanding dust
- Remove loose paint
- Scrub heavy chalk areas and overhead areas such as eaves with soap and water

SURFACE PREPARATION

CONTINUED

- Remove all mildew by washing with a solution of 16 oz (473 mL) liquid household bleach and two oz (59 mL) non-ammoniated liquid detergent per gallon (3.785 L) of water
- Rinse surfaces clean with water and allow to dry for 24 hours
- Prime bare areas with primer specified under **NEW SURFACES**
- **Weathered Aluminum and Vinyl Siding** - Remove dirt and chalk
- Prime with this product
- If chalk remains after cleaning, prime with 6001 Hydrosealer Exterior Primer
- Do not repaint vinyl siding with colors darker than the original color; the siding may warp

NOTE: Blistering and peeling of exterior house paints down to bare wood is usually caused by moisture behind the paint film. Moisture pressure forces the paint away from the surface. Sources of excess moisture in the wood must be eliminated prior to repainting to obtain normal service life of these paints. Old, unsound multiple coat paint systems may be subject to peeling when repainted due to the added weight and stress created by the paint layers. In such cases, all old paint layers must be removed back to the bare wood before repainting.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear an NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

PRECAUTIONS

WARNING! CAUSES EYE, SKIN AND RESPIRATORY TRACT IRRITATION. MAY BE HARMFUL IF SWALLOWED. WHEN TINTED, CONTAINS ETHYLENE GLYCOL WHICH CAN CAUSE SEVERE KIDNEY DAMAGE WHEN INGESTED AND HAS BEEN SHOWN TO CAUSE BIRTH DEFECTS IN LABORATORY ANIMALS. USE ONLY WITH ADEQUATE VENTILATION. KEEP OUT OF THE REACH OF CHILDREN. For emergency information call (800) 545-2643. **Note: These warnings encompass the product series. Prior to use, read and follow product-specific MSDS and label information.** If sanding, wear a dust mask to avoid breathing of sanding dust. Do not breathe vapors or spray mist. Ensure fresh air entry during application and drying. Avoid contact with eyes and skin. If you experience eye watering, headaches, or dizziness, leave the area. If properly used, a respirator may offer additional protection. Obtain professional advice before using. Close container after each use. **FIRST AID:** For skin contact, wash thoroughly with soap and water. If any product remains, gently rub with petroleum jelly, vegetable or mineral/baby oil then wash again with soap and water. Repeat as needed. Remove contaminated clothing. For eye contact, flush immediately with plenty of water for at least 15 minutes. **Get medical attention.** If swallowed, **get medical attention immediately.** If inhalation causes discomfort, remove to fresh air. If discomfort persists or breathing difficulty occurs, get medical attention. **KEEP FROM FREEZING.** DS10-1005

DIRECTIONS FOR USE

TINTING:

Tint the appropriate base with DRAMATONE™ colorants.

SPREADING RATE:

Apply at 500-550 sq ft/gal (12-13 m²/L). Actual coverage may vary depending on surface texture, porosity and application method. For best hiding of bright or accent colors, prime with the appropriate grey base. Certain shades of yellow, orange, pink and red may require multiple coats.

APPLICATION:

Mix thoroughly before use. May be applied by brush, roller or airless spray. No thinning required. For airless spray application, use a .015"-.019" tip at 2000 psi, adjust pressure as needed. Establish that air, surface and material temperatures are above 35°F (2°C) and at least 5°F above the dew point prior to painting. Do not apply at temperatures below 35°F or when temperatures are expected to drop below 35°F within 48 hours of application. Do not apply if rain, snow or heavy dew is expected within 48 hours. On large expanses of metal, temperatures must be 50°F (10°C) or higher. Check temperature requirements on any accompanying primer used.

DRYING TIME:

At 77°F (25°C) and 50% R.H., dries to touch in 30-60 minutes and to recoat in two to four hours. At 35°F (2°C), dries to touch in three to six hours and to recoat in 24 hours. High humidity, thick films or poor ventilation will increase these times.

CLEAN-UP:

Clean hands and tools immediately with warm, soapy water. Clean spills right away with a damp cloth.

SHIPPING

FREIGHT CLASSIFICATION:

Paint, Freezable

PACKAGING:

4 quart (0.946 L)
1 gallon (3.785 L)
5 gallons (18.925 L)

FLASH POINT:

None



Akzo Nobel Paints LLC, Strongsville, Ohio 44136



www.gliddenprofessional.com

LIMITATION OF LIABILITY To the best of our knowledge, the technical data contained herein are true and accurate at the date of issuance but are subject to change without prior notice. We guarantee our product to conform to the specifications contained herein. WE MAKE NO OTHER WARRANTY OR GUARANTEE OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND FITNESS FOR PARTICULAR PURPOSE. Liability, if any, is limited to replacement of the product or refund of the purchase price. LABOR OR COST OF LABOR AND OTHER CONSEQUENTIAL DAMAGES ARE HEREBY EXCLUDED.